

### Product description

	Unit	
• Parquet		Single plank
• V-Groove (GO2)		On 4 sides
• Format (L x w x h)	mm	1900x 190 x 15
• Facing thickness genuine hardwood	mm	3,5
• Core layer	mm	Résineux
• Backing layer	mm	Softwood veneer 2
• Total thickness	mm	15
• Weight	kg/m <sup>2</sup>	8,76
• Moisture content (when delivered)	%	7-10
• Species offered		Oak
• Surface treatment		Oiled
• Packaging		Protective edge with recycled carton (95% recycled paper) Climate protection of PE film
• Packaging contents	pack Pallet	6 planks = 2,166 m <sup>2</sup> 50 packs = 108,3m <sup>2</sup>
• Environnemental prog.		PEFC (Oak)
• Warranty		30 years domestic use (see conditions on berryalloc.com)
• Installation		Rainure-languette (see the installation instructions available on berryalloc.com)
	DTU 51.11	Floating laying (french installation rule)
	DTU 51.2	Glued fitting (french installation rule)
• Underfloor heating		Compatible collé en plain obligatoire (see the specific requirements on berryalloc.com)

Classification	Norm	Unit	Measurements
• Abrasion resistance	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT) Gloss 60°	
• Gloss value			
• Fire class	EN 13 501-1	Oak	Dfl-S1
• Slippery	XP CEN TS 15676	SRT Longitudinal (CV %) SRT Transversal (CV %)	
• Adhesion	ISO 2409	Adhesion	0
• Thermal resistance		coefficient m <sup>2</sup> K/W	Oak: 0,166
• European class (based on unfinished wood)	EN 685	Oak	31
• Loc System Joint strength			
• CE Mark	EN 14342		
• Formaldehyde emission	EN 717-1	µg/m <sup>3</sup>	E1
• VOC emission	ISO 16 000-9	µg/m <sup>3</sup>	A

### Maintenance

See instructions on [berryalloc.com](http://berryalloc.com)

**For commercial use, please take contact with us.**

